

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION  
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification <sup>7</sup> : D03D 15/12, D04B 21/16, A41D 31/00		A1	(11) International Publication Number: WO 00/66823 (43) International Publication Date: 9 November 2000 (09.11.00)
(21) International Application Number: PCT/GB00/01449 (22) International Filing Date: 27 April 2000 (27.04.00) (30) Priority Data: 9909850.1 28 April 1999 (28.04.99) GB (71) Applicant (for all designated States except US): A W HAINSWORTH & SONS LTD [GB/GB]; Spring Valley Mills, Stanningley, Pudsey LS28 6DW (GB). (72) Inventors; and (75) Inventors/Applicants (for US only): HAINSWORTH, Thomas [GB/GB]; The Coach House, St. Annes Hill, St. Annes Lane, Leeds LS4 2SG (GB). WALKER, Derek [GB/GB]; 1 Woodlesford Moor End Road, Halifax HX2 0RR (GB). (74) Agent: BROWNE, Robin, Forsythe; Urquhart-Dykes & Lord, Tower House, Merriion Way, Leeds LS2 8PA (GB).		(81) Designated States: AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, DE, DK, DM, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).  Published With international search report.	
(54) Title: FIRE RESISTANT TEXTILE MATERIAL			
(57) Abstract  A fire resistant textile material comprising a woven faced fabric composed of fibres selected from meta-aramid, polyamideimide and mixtures thereof, the fabric including a woven mesh of strengthening fibres selected from para-aramid, polyparaphenylene terephthalamide copolymer and mixtures thereof.			

*FOR THE PURPOSES OF INFORMATION ONLY*

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

## FIRE RESISTANT TEXTILE MATERIAL

This invention relates to fire resistant textile materials and garments made from these materials. The invention relates particularly but not exclusively to articles of clothing for use by fire fighters and for textiles for manufacture of such clothing.

European legislation requires employers to provide garments which protect their employees against hazards to which they may be exposed. Clothing for protection against heat and flame must pass minimum performance requirements for flame, radiant heat, heat resistance, tensile and tear strength, abrasion resistance and penetration by water and liquid chemicals. The assembled garments must achieve levels of resistance to heat transfer by both flame and radiant heat.

One of the most effective ways to reduce second and third degree burns is to make sure that the barrier of protective clothing between the heat source and the skin remains intact during exposure. This is referred to as the break open resistance or non-break open protection.

An object of the present invention is to optimise thermal protection offered by the fabric. We have discovered that this can be achieved through use of enhanced fabrics design and fibre utilisation.

Outer textile materials for fire fighting clothing have previously been manufactured from 100% meta-aramid or polyamideimide, blends of meta-aramid and para-aramid fibres or by use of core spun yarns or staple mixtures with polyparaphenylene terephthalamide copolymer or fibres comprising para-aramid cores with meta-aramid or polyamideimide covers. The combination of these fibres in the fabric enhances the non-break open protection of the product. However meta-aramid and polyamideimide fibres shrink, consolidate and thicken when exposed to a high temperature heat source. The presence of para-aramid or polyphenylene terephthalamide copolymer in either the fibre blend or as a core can be used to prevent fibre shrinkage and consequent breaking open of the garment. However the inclusion of para-aramid fibre in the blend has been found to be insufficient in tightly woven fabrics to prevent breaking open. Consequently there is a need for improved textile materials for manufacture of fire fighting garments and the like.

Fire fighting garments have been made from a plurality of textile layers, including an outer layer of woven meta-aramid fibre, for example as manufactured under the trade mark Nomex. Break open protection may be afforded by blending with para-aramid fibres, eg as manufactured under the trade mark Kevlar and as disclosed in US 3063966 and US 3506990. However charring of such blends may lead to cracking and embrittlement with consequent deterioration of physical properties.

According to the present invention a fire resistant textile material comprises a woven face fabric composed of fibres selected from meta-aramid, polyamideimide and mixtures thereof, the fabric including a woven mesh of low thermal shrinkage fibres.

Use of low thermal shrinkage fibres in accordance with the present invention increases the residual tensile strength of the textile material following exposure to flame or a radiant heat source. Low thermal shrinkage fibres in accordance with this invention may be defined as a fibre which exhibits not more than 6% shrinkage when exposed to a temperature of 400°C for a period of 5 seconds.

Low thermal shrinkage fibres in accordance with the present invention may be selected from the following materials:

polyparaphenylene terephthalamide (para-aramid eg Kevlar), polyparaphenylene terephthalamide copolymer, polyamide imide, copolyimide, phenolic fibres obtained by cross-linkage of phenolaldehyde resin and containing more than 70% carbon, polybenzimidazole, polyetheretherketone, high tenacity viscose, silicon carbide both with a core and with an organic precursor, ceramic fibres including alumina, alumina silicate and borosilico aluminate; and glass fibres including E glass, C glass, D glass and R glass. Mixtures of the aforementioned fibres may be employed.

Preferred low shrinkage fibres are selected from para-aramid, polyparaphenylene terphthalamide copolymers; polyamide imide; carbon fibres and mixtures thereof.

Fibres or yarns composed of 100% polyparaphenylene isophthalamide meta-aramid (eg Nomex) shrink upon exposure to high temperatures, for example in excess of 295EC. This shrinkage can result in a whole garment exposed to a flame. The low thermal shrinkage fibres, for example para-aramid fibres or yarns do not shrink to the same extent on exposure to this temperature. (The thermal shrinkage of Kevlar is about 3%,

whilst the thermal shrinkage of Nomex is about 24%). If the two fibres or yarns are combined in a fabric, the shrinkage of the fabric may be controlled and/or restricted in such a way that the formation of holes, or break opening, is minimised. The direction of the distortion of the fabric when in the cross-sectional direction when exposed to a high temperature may be controlled so that the fabric becomes thicker. This control is achieved by use of a woven or warp knitted face fabric. This serves to increase the thermal protection afforded by the fabric and increases the number of seconds needed to raise the temperature on the inner side to a level which would create pain or a second degree burn on human skin or on the type of sensor used in Thermal Protection Procedure (TPP) testing.

Fire resistant fabrics in accordance with this invention confer a further advantage in comparison to fabrics composed of an intimate blend of meta-aramid and para-aramid fibres. Fabric formed from an intimate blend exhibits poor retention of the new appearance. The presence of low thermal shrinkage fibres on the surface of a garment, for example Kevlar results in formation of fine fibrils due to abrasion in use. Coloured fabrics, for example dark blue as used for fire fighters' tunics may develop light specks on the surface of the fabric. This gives an uneven appearance on a dark coloured garment. Fabric frosting is the term used to describe this effect.

The low shrinkage fibres are preferably disposed behind the face fabric. This minimises exposure of the strengthening fibres to the heat source.

Fabrics in accordance with the present invention also have the advantage that degradation of the low thermal shrinkage fibres, which are more susceptible to ultra-violet light degradation than other fibres, is reduced because they are not located on the outer surface of the fabric.

In preferred embodiments of the invention the low thermal shrinkage fibres form an interwoven backing scrim on the back of the face fabric. The low thermal shrinkage fibres preferably comprise para-aramid or polyparaphenylene terephthalamide copolymer, eg Kevlar yarns. The thickness of the yarn may be selected in accordance with the resultant mass and weave of the finished fabric. The resultant mass ( $\text{g/m}^2$ ) will vary dependent on the particular end use but will generally be within the range 150 to 300  $\text{g/m}^2$ .

The woven fabric is preferably a combination of a face fabric into which is interwoven a backing scrim. The weave of the face fabric may vary dependent upon the mass and end use required. The interweaving of the backing scrim will be dependent on the weave of the face fabric and the thermal performance required.

Fabrics in accordance with this invention may be produced by interweaving yarns which have been spun and plied or core spun from staple fibres and/or multifilament fibres which may comprise 100% meta-aramid, 100% para-aramid, 100% polyamide imide or intimate blends of any combination of these fibres.

The interweaving of the selected yarns may be such that a closely woven fabric suitable for use as the outer face of a garment is combined with a loosely woven fabric which is suitable for use as the reverse side of the garment.

The selection of fibres and yarns which may be incorporated into fabrics in accordance with this invention will take account of the different shrinkage properties of these fibres and the particular requirements of the final fabric. A combination of high and low shrinkage fibres may be chosen. For example meta-aramid face fabric with a thermal shrinkage of approximately 24% and a para-aramid backing scrim or mesh with a thermal shrinkage of approximately 3 % may be employed.

The proportion and count of face side yarns to reverse side yarns may be determined by the required weight of the final fabric, the interlacing of the face weave and the degree of effectiveness required from the properties of the reverse side yarn.

In a preferred embodiment the face yarns count may be in the range of resultant 15 to 50 Nm (Numero metric, including single or multiple folding of yarns), preferably 20 to 41 Nm. The reverse side yarns count may be in the range 25 to 150 Nm, preferably 40 to 60 Nm (Numero metric, including single or multiple folding of yarns).

Independently the proportion or ratio of face to back yarns by number may be 1 to 20:1, preferably 6 to 12:1.

The interlacing of the face weave may be determined by the desired appearance and the physical properties required of the final fabric. This interlacing may be any of a number of designs known to those skilled in the art. The preferred face weaves are plain weave, plain weave rip stop, twill weave rip stop or straight twill weaves and their

derivatives. Figure 1 shows weaving plans for five preferred fabrics. Plan 1 is a plain weave face; plan 2 is a plain weave rip stop face; plan 3 is a 2 x 2 twill face; and plan 4 is a 2 x 1 twill rip stop face. With these constructions the proportions of warp and weft yarns may be more evenly distributed to afford a more balanced structure. Other weaves may be used if the requirements to do so arises. The degree of interlacing between the face side yarns and the reverse side yarns is important to achieve a fabric which maximises the different properties of these yarns, gives a level surface and pleasing appearance and yet can be woven with the highest possible efficiency.

In a preferred method the yarns for the warps of both the face and reverse sides of the fabric may be assembled in the specified proportions and order of working by the sectional warping process onto one or two warped beams jointly having the total number of ends required to weave the final fabric.

The weft yarns may be inserted across and interlaced with the warp yarns in the specified proportions, order of working and density selected to produce the required face and reverse side weaves.

Differential tension may be applied to the face and reverse side yarns during the weaving process and during the insertion of the weft. This is important to compensate for the varying degrees of elongation which are inherent in the different types of fibres used in those yarns and which are important to the properties of the fabric of this invention.

A preferred weaving machine which may be used to produce fabric of this invention is one that will supply the face and back warp yarns from individual warp beams at different fed rates to compensate for the varying degrees of elongation and the varying inter-lacings of the face fabric yarns and reverse side yarns.

A preferred weaving machine should also have electronic filling control braking for independent weft tensioning to compensate for the varying degrees of elongation and the varying inter-lacings of the face fabric yarns and reverse side yarns. The differential tensioning set to weave fabric of this invention may require a breaking force of 35% for the face yarn and 75% for the reverse side yarn.

Warp knitted fabrics may also be provided in accordance with this invention.

Previously known fire fighting garments comprise a composite of three textile

layers, an outer fabric, a moisture barrier and a quilted thermal lining. The present invention may reduce the need for use of three layers, or allow the total weight of those three layers to be reduced.

The invention is further described by means of example but not in any limitative sense

#### Example 1

A textile material in accordance with the present invention (referred to as specification EX276) was woven using a self-stitched double construction, with a blend of 93% meta-aramid, 5% para-aramid and 2% antistatic fibre (Nomex Delta C) 2 by 1 twill face and a 100% para-aramid (Kevlar) plain weave back. It is woven in the proportion of six face threads to one back thread.

#### Test Method

The fire resistance of textile materials in accordance with the present invention was determined using the following test method.

The Thermal Protective Performances of fabrics in accordance with this invention were measured by the Thermal Protective Performance (TPP) test. This test is a laboratory test to assess how well a fabric or combinations of fabric provides a barrier to and insulation from heat/flame.

In a "typical" flash fire the heat flux may be in the region of 80 kW/m<sup>2</sup>. The test method used a heat source with a heat flux of 80 kW/m<sup>2</sup> (2 cal/cm<sup>2</sup>/sec) made up of approximately 50% radiant and 50% convective heat exposed to the underside of the sample. Sensors are employed to measure a rise in temperature on the other side of the sample. This rise in temperature is correlated, via earlier research work, to the tolerance of human skin and susceptibility to pain and second degree burns as used in TPP testing where "Stoll Curves" are used for the correlation.

The TPP test was used to measure heat energy required on outer surface (underside) of fabric or fabric combination to cause second degree burns at the back of the fabric or fabric combination. The number of seconds required with a fixed level of energy



(2 cal cm<sup>2</sup>sec<sup>-1</sup>) to reach pain and second degree burns is also determined.

TABLE I

Description of Fabric Assembly	Pain (/sec)	2 <sup>nd</sup> degree burn (sec)	TPP (Wcm <sup>-2</sup> )	Fabric & Fibre Factor
EX276 (219 g/m <sup>2</sup> )				
PTFE membrane laminated to aramid felt (Goretex E89)				
aramid felt (Nomex Felt)				
aramid liner (Nomex III)				
<b>Total weight: 620 g/m<sup>2</sup></b>	14.5	20.9	41.9	6.8
Quality 1166 Nomex Delta C (219 g/m <sup>2</sup> )				
Goretex E89				
Nomex Felt				
Nomex III				
<b>Total weight: 620 g/m<sup>2</sup></b>	13.0	18.3	36.5	5.8
Quality 1186 PBI Gold (224 g/m <sup>2</sup> )				
Goretex E89				
Nomex Felt				
Nomex III				
<b>Total weight: 625 g/m<sup>2</sup></b>	13.2	19.5	39.1	6.3
Quality 1191 Nomex Delta T (219 g/m <sup>2</sup> )				
Goretex E89				
Nomex Felt				

Nomex III				
Total weight: 620 g/m <sup>2</sup>	13.5	19.5	39	6.3

The results are shown in Table 1. These indicated that the energy required to give second degree burns at the back of the fabric was approximately 14.8% higher for the textile material in accordance with the present invention referred to as quality EX276 than a fabric of equivalent weight (Quality 1166) manufactured solely from the same intimate blend of fibres as the face fabric of EX276.

## CLAIMS

1. A fire resistant textile material comprising a woven faced or warp knitted fabric composed of fibres selected from meta-aramid, polyamideimide and mixtures thereof, the fabric including a woven mesh back of low thermal shrinkage fibres.
2. A textile material as claimed in claim 1, wherein the low thermal shrinkage fibres are selected from fibres having a shrinkage of less than 6% at 400°C
3. A textile material as claimed in claim 2, wherein the low thermal shrinkage fibres are selected from polyparaphenylene terephthalamide (para-aramid eg Kevlar), polyparaphenylene terephthalamide copolymer, polyamide imide, copolyimide, phenolic fibres obtained by cross-linkage of phenolaldehyde resin and containing more than 70% carbon, polybenzimidazole, polyetheretherketone, high tenacity viscose, silicon carbide both with a core and with an organic precursor, ceramic fibres including alumina, alumina silicate and borosilico aluminate; and glass fibres including E glass, C glass, D glass and R glass and mixtures thereof.
4. A textile material as claimed in any preceding claim wherein the low thermal shrinkage fibres are disposed behind the face fabric.
5. A textile material as claimed in any preceding claim, wherein the low thermal shrinkage fibres form an interwoven backing scrim on the face fabric.
6. A textile material as claimed in any preceding claim, wherein the low thermal shrinkage fibres comprise para-aramid yarns.
7. A textile material as claimed in any preceding claim, wherein the mass of the textile material is within the range 150 to 300 g/m<sup>2</sup>.

8. A textile material as claimed in any preceding claim, wherein the woven fabric is a combination of a face weave on which fabric is interwoven using a backing scrim.

9. A woven textile material as claimed in any preceding claim, wherein the face yarns count is in the range of resultant 15 to 50 Nm.

10. A woven textile material as claimed in claim 9, wherein the face yarns count is in the range of resultant 20 to 41 Nm.


11. A woven textile material as claimed in claim 9 or 10, wherein the reverse side yarns count is in the range 25 to 150 Nm.

12. A woven textile material as claimed in claim 11, wherein the reverse side yarns count is in the range 40 to 60 Nm.


13. A woven textile material as claimed in any of claims 9 to 12, wherein the ratio of face to back yarns by number is in the range 1:1 to 20:1.

14. A woven textile material as claimed in claim 13, wherein the ratio of face to back yarns by number is in the range 6:1 to 12:1.


15. A woven textile material as claimed in any preceding claim, wherein the face weave is selected from: plain weave, plain weave rip stops, straight twills, twill weave rip stops and their derivatives.




Plan no. 1




Plan no. 2



Plan no. 3



Plan no. 4



Plan no. 5

FIG. 1

# INTERNATIONAL SEARCH REPORT

International Application No

PCT/GB 00/01449

## A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 D03D15/12 D04B21/16 A41D31/00

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 D03D D04B A41D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	DE 296 11 356 U (SEIZ) 5 September 1996 (1996-09-05) claim 1	1-6, 8, 15
A	US 5 691 040 A (BARBEAU) 25 November 1997 (1997-11-25) column 2, line 30 - line 43	1, 3, 7, 9, 10, 15
A	WO 99 16957 A (DU PONT DE NEMOURS) 8 April 1999 (1999-04-08)	

☐

Further documents are listed in the continuation of box C.

☒

Patent family members are listed in annex.

### \* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

31 July 2000

Date of mailing of the international search report

04/08/2000

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl.  
Fax: (+31-70) 340-3016

Authorized officer

Boutelegier, C

# INTERNATIONAL SEARCH REPORT

information on patent family members

International Application No

PCT/GB 00/01449

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
DE 29611356 U	05-09-1996	NONE	
US 5691040 A	25-11-1997	NONE	
WO 9916957 A	08-04-1999	AU 9777798 A	23-04-1999